


BGG29 (1mm thick)



Glass Type	Refractive Index, n_e (n_d)	Density, (g/cm^3)	Thermal Expansion, $\alpha_{20-120} 10^7 C^{-1}$	Annealing Temperature, $^{\circ}C$	Close to Schott Glass
BGG29	1.56	2.8	113		S8612